


Thermally conductive EMI absorbers are a hybrid of classic gap pad material as well as components that have absorbent properties.

They have a thermal conductivity of 2,0 W/m*K and are available in material thicknesses from 0,5 to 12 mm. The TCMWA series can be supplied as standard sheets or customized stampings, making them suitable for a wide range of applications.

- Thermal conductivity: 2,0 W/m*K
- Excellent absorption characteristics
- Naturally tacky
- Reworkable
- Sheet form
- Die-cut parts




PRODUCT SPECIFICATIONS

PROPERTY	VALUE / TOLERANCE	TEST METHOD
Basic material	Silicone	-
Thermal conductivity	2,0 W/m*K	ASTM D5470
Hardness	40 Shore 00	ASTM D2240
Density	4,4 g/cm ³	ASTM 792
Temperature range	-60 to 180 °C	internal
Flammability rating	V-0	UL94*
Colour	Dark Gray	Visual
EMI Attenuation @5 GHz	21 dB/cm	internal
EMI Attenuation @7 GHz	27 dB/cm	internal
Volume resistivity	> 10 ¹² Ω*m	ASTM D257
Thermal impedance@10psi	0,76 °C-in ² /W	ASTM D5470
Thermal impedance@30psi	0,61 °C-in ² /W	ASTM D5470
Thermal impedance@50psi	0,53 °C-in ² /W	ASTM D5470
Thickness range	0,5 – 12 mm	-
Total mass loss (TML)	0,14%@24h / 150°C	-


* tested according to UL94 V-0

Please note: Picture only shows an example of an absorber pad.

DEFLECTION VS PRESSURE




THERMAL IMPEDANCE VS PRESSURE



Modifications and errors excepted. The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verifications and testings to determine the suitability for their own particular purpose of any information or products referred to herein.

REFLECTIVITY PERFORMANCE



Modifications and errors excepted. The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verifications and testings to determine the suitability for their own particular purpose of any information or products referred to herein.